

## **Boron Nitride Grade M & M26**

Boron Nitride is an advanced synthetic ceramic material available in powder, solid, liquid and aerosol spray forms. Its unique properties - from high heat capacity and outstanding thermal conductivity to easy machinability and superior dielectric strength - make boron nitride a truly outstanding material.

Solid Boron Nitride Grade M is a truly hydrophobic advanced ceramic. Composed of boron nitride and silica, it is completely resistant to moisture and has a MIL-I-10A grade of L542, a test requiring immersion in water for 48 hours prior to testing at elevated frequencies. Grade M is suitable for the most severe electrical applications. It is an excellent refractory material at temperatures up to 1400°C, and is unparalleled in resistance to thermal shock.

## **Applications**

- High temperature electrical insulators and vacuum furnace supports which require electrical resistivity, high temperature strength, thermal shock resistance and low chemical resistivity
- Crucibles and containers for high purity molten metals
- Tools and refractories for glass forming which provide non-wetting, non-B2O3 containing contacts
- Radar components and antenna windows which require exacting electrical and thermal properties

Typical Properties					
Typical Chemical Analysis	Grade M	Grade M26			
Boron <sup>1</sup>	18-20.25%	26.5-28.7%			
Nitrogen <sup>1</sup>	22.5-25.5%	32.8-35%			
Oxygen <sup>1</sup>	-	-			
Calcium <sup>1</sup>	.01%3	.01%3			
Silica (SiO <sub>2</sub> ) <sup>1</sup>	60%	40%1			
Other Inorganic <sup>1</sup>	.02%	.05%			
Trace Metals	.05%	.05%			
TOTAL	100%	100%			
B <sub>2</sub> O <sub>3</sub> *	.2%	.2%			

\*B203 is given for clarification and is not part of the elemental analysis 1 Wet Chemistry - 2 LECO Oxygen - 3 Optical Emission Spectroscopy

Typical Physical Properties					
Typical Physical Properties	Grade M		Grade M26		
Percent BN:	40		60		
Percent SiO2:		40 60  60 40  Parallel Perpendicular Parallel Perpen 1,7x10 <sup>15</sup> 5.1x10 <sup>15</sup> 6.4x10 <sup>14</sup> 2.9x1 2.4x10 <sup>13</sup> 3.3x10 <sup>13</sup> 2.4x10 <sup>13</sup> 8.5x1  4.21 3.87 4.48 3.8 3.86 4.08 3.89 4.2  tth: volts/mil & (volts/mm)		10	
	Parallel I	Perpendicular	Parallel	Perpendicular	
Volume Resistivity (ohm-cm) @RT: @150 <sup>0</sup> C:	1.7X10 <sup>15</sup> 2.4X10 <sup>13</sup>			2.9x10 <sup>15</sup> 8.5x10 <sup>13</sup>	
Dielectric Constant (@ IMHz) @RT: microwave frequency: @ RT, 8.8 GHz:		. ,		3.89 4.28	
Dielectric Strength: volts/mil & (volts/mm)					
Sample thickness: 10 mil Tested up to 25kV) 25 mil	1670 (65748) >1000 (>39370)		1690 (66535) >1000 (>39370)		
Dissipation Factor (Loss tangent)					
@RT @ 1MHz @150 <sup>0</sup> C @ 1MHz @RT @ 8.8GHz	.0016 .0017 .0011	.0035 .0055 .0005	.0017 .0094 .0039	.0061 .0062 .0006	
Loss Factor @RT @ 1MHz @150 <sup>0</sup> C @ 1MHz @RT @ 8.8GHz	.0067 .0077 .0042	.0140 .0230 .0020	.0076 .0440 .0150	.0230 .0250 .0260	
Surface Resistivity (ohms/) @ RT @ 150 <sup>0</sup> C	8.5 x 10 <sup>16</sup> 1.4 x 10 <sup>15</sup>		4.2 × 10 <sup>16</sup> 1.5 × 10 <sup>15</sup>		

The values presented are mean and typical of those resulted from test samples. They are provided as an indication only to serve as guidance in the design of ceramic components and are not guaranteed in any way. The actual values can vary according to the shape and size of the envisaged component.



## **PRECISION CERAMICS**